



Continuously TTT-diagram of C 60E (Ck60)

Temperaturen in °C

Härtetemperatur im Stirnabschreckversuch	normalizing	hardening	Abschreckmittel	annealing
830	820 – 860	800 – 840	Öl oder Wasser	550 – 660

Normalizing- hardening and annealing temperature of C 60E (Ck60)