

Porosity in root of bend test. Welded with E7018 stored in a holding oven that was turned off to save electricity.

Al Moore 2005

