

<u>Melt#</u>	<u>Quantity</u>	<u>Date</u>	<u>Lot/Serial.:</u>	<u>Specification</u>
996T	1	9/14/11	996T - -	ASME SA494-10

C H E M I C A L S

C : .169 SI: .98 MN: .987 P : .001 S : .006
 CU: 32.32 NB: .13 FE: 1.64

NI: BALANCE

M E C H A N I C A L S

ULTIMATE TENSILE S 80 KSI YIELD STRENGTH .2% 31 KSI
 ELONGATION 44 %